

TQ CEMPOINT

PRODUCT DATASHEET

PUMPABLE MASONRY MORTAR

Pointing Mortar is a premixed, gun injection mortar that provides a clean, quick, lasting solution for pointing sound brickwork, natural stone or masonry.

Formulated to conform with BS EN 998-2:2016 - Masonry Mortar their graded aggregates combined with fast setting additives ensure rapid hardening, high early strength that only requires the addition of water on site.

All surfaces must be clean, free of dust and any other loose material. Pre-dampen the surface with clean water allow to dry ensuring no standing water is visible during application. For very absorbent surfaces please contact TQ Support.

TECHNICAL DATA

WATER DEMAND	3.0L to 3.5L of water per 25kgs
WORKING TIME	30 MINUTES
JOINT WIDTH & DEPTH	5MM & 75MM
SUBSTRATE TEMPERATURE	+3 °C MIN / + 25 °C MAX
AIR TEMPERATURE	+5 °C MIN / + 25 °C MAX
DENSITY	1500KG/M ³
COMPRESSIVE STRENGTH	>5 N/ mm ² 28 DAYS

MIXING

3L to 3.25L of water per 25kgs to achieve the desired workability and ensure consistent water content for each batch. Only mix the amount of material that can be used within the working time. Mix with a suitable mechanical mixer. Do not remix or add water after the mixing process, this will alter the strengths and effect the products overall performance.

APPLICATION

Keeping the nozzle just clear of the wall, inject the mortar into the joint, slightly overfilling, working from the top wall downwards. The mortar should be tooled off after its initial sheen. The time this takes depends upon the absorbency of the masonry.

Tools should be washed with water immediately after use.

STANDARD COLOURS AVAILABLE

Standard range of colours are available from stock. Bespoke blends/colour matches are also available on request.

QUALITY

UKCA Marking
0086-CPR-755318
BS EN 998-2:2016 - Masonry Mortar

ISO 9001:2015
FM 33290

FOR FURTHER INFORMATION CONSULT OUR TECHNICAL DEPARTMENT

The information and recommendations above are given in good faith based on our current knowledge and experience of the products when properly stored, handled and applied in accordance with current best practice, national standards and our recommendations. As we have no control over site conditions or methods of application, no liability can be derived from the contents of this information sheet, or from any written recommendations, or from any other advice offered. The user of the product is solely responsible for the product's suitability for the intended application and is recommended to test the suitability prior to use. We reserve the right to change the properties of our products without notice.

TILlicOUNTRY QUARRIES
RWM House,
Killbagie, Alloa,
FK10 4DY

T: 01259 730 481
E: sales@tillicountryquarries.com
tillicountryquarries.com

TILlicOUNTRY QUARRIES
MORTARS AND RENDERS
Hullerhill, Kilwinning,
Ayrshire, KA13 7QN

T: 01294 557 515
E: sales@tillicountryquarries.com
tillicountryquarries.com